

	INDICE DE PLASTICIDAD	17.927
	LIMITE LIQUIDO	36.889
	LIMITE PLASTICO	18.962
m	CONTENIDO DE HUMEDAD	27.925
-0.5122	LIMITE DE RETRACCIÓN	15.025
b		
49.694	W Fab (%)	25
	a	36.889
	b	18.962
	c	17.927
	d	12.670
	e	6.630
	LR	12.330



Feb, 2018