

Anexo A

Resultados obtenidos por (Torres, 2021)

Comparación de muestras					
Muestra	N	N + 10% C.R.	N + 15% C.R.	N + 20% C.R.	% promedio mejoramiento
<i>Límites de Atterberg</i>					
LL [%]	38	37	35	34	
		-2.63%	-7.89%	-10.53%	-7.02%
LP [%]	25	26	26	27	
		4.00%	4.00%	8.00%	5.33%
IP	13	11	9	7	
		-15.38%	-30.77%	-46.15%	-30.77%
<i>Proctor modificado</i>					
$\rho_{maxseca}$ [gr/cm ³]	1.796	1.801	1.92	2.127	
		0.28%	6.90%	18.43%	8.54%
W _{optima} [%]	13	12.1	11.6	9.1	
		-6.92%	-10.77%	-30.00%	-15.90%
<i>CBR</i>					
CBR _{100%} [%]	20.4	25.6	30.1	40.9	
		25.49%	47.55%	100.49%	57.84%
CBR _{95%} [%]	15.6	15.7	21.3	28.5	
		0.64%	26.76%	45.26%	24.22%

Nota. N: Suelo en estado natural. % C.R.: Porcentaje de dosificación de concreto reciclado